

Information

Compressibility, softness and durability allow BF-1000 to adapt to various environments, making it an ideal choice for sealing outdoor enclosures, protecting electronics from shock and heat, and providing cushioning or vibration isolation for various applications. BISCO® Silicones are available in various thicknesses and manufactured in roll form to allow fabricators to easily convert the material to the proper dimensions.

Features and benefits

- Excellent memory and low stress relaxation reduces maintenance costs associated with gasket failures due to compression set and softening.
- Softness allow designers to use less force to seal enclosures and still protect their device from the environment.
- High compressibility allows material to conform to variable width gaps and awkward shapes, thereby allowing engineers more design flexibility.
- Resistance to ultraviolet light, ozone, extreme temperatures, and flame enables consistent performance in all environments.

Applications

- Environmental seals to protect against penetration of dust, moisture, air, or light within outdoor enclosures such as lighting fixtures, HVAC units, and electronic cabinets.
- Vibration isolation in electronic components and transportation vehicles.
- Fire retardent thermal insulation

Installation

- Available with a pressure-sensitive adhesive on one or two sides to allow easy application to a variety of surfaces.

Physical

| PROPERTY | TEST METHOD | TYPICAL VALUE |
|--|---|--|
| Colour | | Grey* and white |
| Thickness inches (mm) Tolerance | | 0.062 - 1.00 (1.6 - 25.4) see below |
| Standard width inches (mm) | | 36 (914) |
| Density, lb.ft ³ (kg/m ³) | ASTM D 1056 | 13 (208) |
| Compression force deflection psi (kPa) | Force measured @ 25% deflection ASTM D 1056 | 3 (20.7) |
| Compression set % max | ASTM D 1056 Test D @ 158°F (70°C), 22hrs ASTM D 1056 Test D @ 212°F (100°C), 22hrs | < 1 < 5 |
| Tensile strength, psi (kPa) | ASTM D 412 | 35 (241) |
| Elongation % | ASTM D 412 | 90 |

*Grey colour is standard in 0.062 (1.9mm), 0.250 (6.4mm) and 0.500 (12.7mm) thicknesses.

Flammability & Outgassing

| PROPERTY | TEST METHOD | TYPICAL VALUE |
|--------------------------------------|--|---------------------|
| Flame resistance | UL 94 | Listed V-0 and HF-1 |
| Flame spread index (L _s) | ASTM E 162 | < 35 |
| Smoke Density (D _s) | ASTM E 662 Tested @ 4.0 minutes Tested @ 1.5 minutes | < 50 < 20 |
| Toxic gas emissions rating | SMP-800C & BSS 7239 | Pass |

Environmental Properties

| PROPERTY | TEST METHOD | TYPICAL VALUE |
|---|-----------------------------|----------------|
| Water absorption | Internal: 24hrs @ room temp | 3.50 % |
| UV resistance | SAE J- 1960 | No degradation |
| Ozone effect rating | ASTM D 1171 | 0 (no cracks) |
| Corrosion resistance | AMS - 3568 | Pass |
| Meets requirements of FDA CFR 177.2600 for Food Contact | | BF-1000 white |
| Other specifications available | BMS 1-68 | |

Electrical & Thermal Properties

| PROPERTY | TEST METHOD | TYPICAL VALUE |
|---|-----------------------|------------------|
| Dielectric constant | ASTM D 150 | 1.34 |
| Dielectric strength | ASTM D 149, volts/mil | 89 |
| Dry arc resistance | ASTM D 495, seconds | 90 |
| Volume resistivity, Ohm - cm | ASTM D 257 | 10 ¹⁴ |
| Thermal conductivity, BTU in/hr/ft ² /°F (w/m °K) | ASTM C 518 | 0.39 (0.06) |

Temperature Resistance

| PROPERTY | TEST METHOD | TYPICAL VALUE |
|---|-------------|-------------------------|
| Low temperature flex at -67°F (-55°C) | ASTM D 1056 | Pass |
| Recommended temperature °F (°C) | SAE J-2236 | -67 to 392 (-55 to 200) |
| Recommended intermittent high temperature use °F (°C) | Internal | 482 (250) |

| STANDARD THICKNESS | | TOLERANCE (INCHES) |
|--------------------|-------|-----------------------|
| INCHES | MM | |
| 1/16 | 0.062 | 1.57 ± 0.016 |
| 3/32 | 0.094 | 2.39 ± 0.020 |
| 1/8 | 0.125 | 3.18 ± 0.025 |
| 3/16 | 0.188 | 4.76 ± 0.030 |
| 1/4 | 0.250 | 6.35 ± 0.040 |
| 3/8 | 0.375 | 9.53 ± 0.060 |
| 1/2 | 0.500 | 12.70 ± 0.050 |
| 3/4 | 0.750 | 19.05 ± 0.090 |
| 1 | 1.000 | 25.40 ± 0.090 |

The information and data contained herein is believed to be accurate and reliable. However it is the user's responsibility to determine suitability for use. C B Frost & Co makes no warranties concerning fitness or suitability of its products for a particular use or purpose. C B Frost & Co reserve the right to alter the material specification at any time, without prior notice.

Notes

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.

t +44 (0) 121 773 8494
f +44 (0) 121 772 3584
w www.cb frost-rubber.com
e info@cb frost-rubber.com
t twitter.com/cbfrost